

# E6013 Mild Steel Welding Electrode

This E6013 welding electrode is designed for welding mild steel. It offers excellent welding performance with a stable arc, minimal spatter, and easy slag removal.



## ADDITIONAL IMAGES



## Product Overview

**MT-12** CORRESPONDING TO **AWS E6013**  
**GB 5118**

**ELECTRODE FOR WELDING MILD STEEL**

**Description:**  
MT-12 is low carbon steel electrode with flux coating. It has excellent welding performance. The arc is stable and the spatter rate is negligible. The slag is fluid and easy to remove. It is suitable for all position welding of steel plates and irregular joints under normal conditions.

**Applications:**  
For welding structure of steel sheets, vessels, machinery, automobile and other applications.

**Chemical Composition of Weld Metal (%)**

	C	Mn	Si	S	P
MINIMUM	0.08	0.20	0.03	0.005	0.005
TYPICAL	0.10	0.40	0.05	0.008	0.008

**Mechanical Properties of Weld Metal**

Property	Standard	Requirement	Standard	Requirement
Yield Strength	MPa	≥ 355	MPa	≥ 355
Tensile Strength	MPa	≥ 420	MPa	≥ 420
Elongation	%	≥ 22	%	≥ 22

Product is certified by ABS, BV, CCS, DNV, GL, LR, NK.

Technical overview and performance characteristics of the E6013 welding electrode.

## High-Performance Mild Steel Welding Electrode

This E6013 welding electrode features a titania coating designed for superior performance in mild steel welding applications. It ensures a stable arc with negligible spatter, resulting in smooth, professional-grade weld appearances. The fluid slag is easily removed after hardening, making it ideal for all-position welding, including irregular joints and challenging conditions.

## Standards & Certifications

### International Approvals

ABS • BV • CCS • DNV • GL • LR • NK

### Compliance Standards

AWS A 5.1 E6013, GB/T5117 E4313, JIS Z3211 E4313

## Technical Specifications

### Chemical Composition of Weld Metal (%)

Element	Typical Value
Carbon (C)	0.09
Manganese (Mn)	0.40
Silicon (Si)	0.20
Sulfur (S)	0.015
Phosphorus (P)	0.019

### Mechanical Properties

**400 MPa**

Yield Strength

**490 MPa**

Tensile Strength

**29 %**

Elongation

**70 J**

Charpy V Impact (0°C)

## Operational Guidelines

### Recommended Current

- DC: 80-120 A
- AC: 90-130 A

### Storage Requirements

Keep dry and protect from humidity to maintain electrode integrity.

## Logistics

### Packaging

Cartons of 20kg net each. Configuration: 8 boxes x 2.5kg (for 2.5mm size) or 4 boxes x 5kg (for other sizes). Pallet options available upon request.